



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011

FAX 82-2-2634-1008

Report No : TAK-2025-021451
 Representative : Lee Young-jun, Shin Dong-bin
 Company name : LOTTE CHEMICAL Corp.
 Address : 300, Olympic-ro, Songpa-gu, Seoul, Republic of Korea

Receipt Date : 2025.02.07.
 Test Completion Date : 2025.02.21.

Sample name : Solid Surface[STARON]

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Specific Gravity((23/23) °C)(Method A)	-	-	1.75	ASTM D792-20
Water Absorption(24 h Immersion)	%	-	0.02	ASTM D570-22
Barcol Hardness	-	-	63	Client Provided Test Method(ASTM D2583-13a)
Rockwell Hardness(HRM)(Procedure A)	-	-	82	ASTM D785-23
IZOD Pendulum Impact Resistance(Method A)	J/m	-	15	ASTM D256-23e1
Tensile Strength(**)	MPa	-	35.0	ASTM D638-22
Flexural Strength(***)	MPa	-	54.4	ASTM D790-17
Flexural Modulus of Elasticity(***)	GPa	-	9.36	ASTM D790-17
Thermal Expansion	1/°C	-	5.8×10^{-5}	applied KS M 3015 : 2003
Temperature Under Flexural Load(Method B, 1.82 MPa)	°C	-	95	ASTM D648-18
Appearance(Crack) after Heat Resistance[(170 ± 2) °C × 1 h]	-	-	No defects	By the Client
Appearance after Hot Water Resistance(****)	-	-	No defects	By the Client
Dropping Impact Test(****)	-	-	No Defects	Client Provided Test Method

- Next Page -

Seungyeob Lee

Prepared by Seungyeob Lee
 Tel : 02-2092-3645

Kyoung-Mun KIM

Reviewed by Kyoung-Mun KIM
 Tel : 1577-0091(ARS ①-④)

2025.02.21

Korea Testing & Research Institute

President



QR Code for forgery

Page : 1 of 2

전자문서본은 시험결과에 대한 참고용입니다.

전자문서본(Electronic Copy)



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-2-2164-0011

FAX 82-2-2634-1008

Report No : TAK-2025-021451
Representative : Lee Young-jun, Shin Dong-bin
Company name : LOTTE CHEMICAL Corp.
Address : 300, Olympic-ro, Songpa-gu, Seoul, Republic of Korea

Receipt Date : 2025.02.07.
Test Completion Date : 2025.02.21.

Sample name : Solid Surface[STARON]

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
-----------	------	--------	--------	-------------

** Specimen: Type III, Speed of Testing: 5 mm/min
 *** Support Span: 194 mm, Speed of Testing: 5.2 mm/min
 **** Drop Height: 2 m, Drop Weight: 112 g(Steel Ball), Test Surface: Concrete, Appearance: Crack or Not
 ***** Changing appearance(Crack) after pouring boiled water on the surface of the specimen

- Usage of Report : QUALITY CONTROL

- Note :
1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
 2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
 3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Seungyeob Lee

Prepared by Seungyeob Lee
Tel : 02-2092-3645

Kyoung-Mun KIM

Reviewed by Kyoung-Mun KIM
Tel : 1577-0091(ARS ①→④)

2025.02.21

Korea Testing & Research Institute

President



QR Code for forgery